

**Sintered Silicon Carbide Ceramic**  
 Technical Parameter of SSIC products

Item	Unit	Data
temperature of application	°C	1600
density	g/cm <sup>3</sup>	>3.1
open porosity	%	<0.1
bending strength	Mpa	>400
	Mpa	
modulus of elasticity	Gpa	420
	Gpa	
thermal conductivity	W/m.k	74
coefficient of thermal expansion	k <sup>-1</sup> × 10 <sup>-6</sup>	4.1
Vickers Hardness HV <sub>10</sub>	Gpa	22
acid-proof alkaline		Excellent

The values for above are the typical result from the test,not the promised exactly data applied to all orders

Website:

<http://www.advanceceramic.net>

Email:

info@advanceceramic.net